

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
10 March 2005 (10.03.2005)

PCT

(10) International Publication Number
WO 2005/021851 A1

(51) International Patent Classification⁷: **D03D 47/23**, (74) Agent: **HEYDE, Katrien**; Bekaertstraat 2, B-8550 Zwevegem (BE).
47/12

(21) International Application Number:
PCT/EP2004/051998

(22) International Filing Date:
2 September 2004 (02.09.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
03103277.4 3 September 2003 (03.09.2003) EP

(71) Applicant (for all designated States except US): **NV Bekaert SA** [BE/BE]; Bekaertstraat 2, B-8550 Zwevegem (BE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **OSSELAER, Peter** [BE/BE]; Koestraat 76, B-9700 Oudenaarde (BE). **SERCU, Marc** [BE/BE]; Hof van 1 Henneken 31, B-8800 Roeselare (BE). **PAPPAERT, Wim** [BE/BE]; Ruisbroeksesteenweg 111, B-1600 Sint-Pieters-Leeuw (BE). **VAN DAMME, Filip** [BE/BE]; Gampelaerreedreef 62, B-9800 Deinze (BE).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.


(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: **COATED RAPIER**



WO 2005/021851 A1

(57) Abstract: The invention relates to a rapier coated at least partially with a hard metal based coating, said coating having a hardness higher than 1000 Vickers. Possibly, the rapier is further coated with a hard carbon coating on top of this hard metal based coating. The invention further relates to a method of manufacturing a coated rapier.

WO 2005/021851

PCT/EP2004/051998

Coated rapier.**Field of the invention.**

5 The invention relates to a rapier coated with a hard metal based coating and to a method of manufacturing such a coated rapier.

Background of the invention.

10 In a weaving machine, a rapier is used for the picking of a thread across the width of the weaving machine.
The portions of the rapier coming into sliding contact with the treads suffer from frictional abrasion by the threads.

Summary of the invention.

15 It is an object of the present invention to provide a rapier with a high wear resistance and an improved durability.

According to a first aspect of the present invention, a rapier coated at least partially with a hard metal based coating is provided. The hard metal based coating has a hardness higher than 1000 Vickers. More preferably, the hard metal based coating has a hardness higher than 1200 Vickers or higher than 1400 Vickers.

20 Hard metal based coatings comprise for example metal carbides, metal nitrides and metal oxides, such as tungsten carbide, titanium carbide, chrome nitride, aluminium oxide, chrome oxide, ...

25 Hard metal based coating according to the invention can be deposited by any technique known in the art. However, the hard metal based coating is preferably deposited by thermal spraying.
Thermal sprayed coatings are characterised by a surface roughness Ra between 2 and 5 μm .
30 The term Ra is defined as the arithmetical mean deviation of the profile.

WO 2005/021851

PCT/EP2004/051998

2

The hard metal based coating preferably has a thickness ranging between 10 and 500 μm . More preferably, the hard metal based coating has a thickness between 30 and 200 μm , as for example 100 μm .

5

In a preferred embodiment the hard metal based coating is further coated with a hard carbon coating on top of the hard metal based coating.

Preferred hard carbon coatings comprise diamond-like coatings.

10

Diamond-like coating are amorphous carbon based coatings with a high hardness and a low coefficient of friction. Their unique composition and structure results in excellent wear resistance and non-sticking characteristics.

15

Diamond-like coatings comprise for example diamond-like carbon (DLC) coatings and diamond-like nanocomposite (DLN) coatings or layered structures of diamond-like carbon (DLC) and diamond-like nanocomposite (DLN) coatings.

20

Diamond-like coating comprise for example diamond-like carbon (DLC) coatings and diamond-like nanocomposite (DLN) coatings.

25

Diamond-like carbon coatings comprise amorphous hydrogenated carbon coatings (a-C:H); whereas diamond-like nanocomposite coatings comprise interpenetrating networks of a-C:H and a-Si:O. A representative DLN coating comprises 30 to 70 at% C, 20 to 40 at% H, 5 to 15 at% Si and 5 to 15 % O.

DLN coatings exhibit a very low coefficient of friction, even in high humidity or wet environment.

30

To influence its conductivity, the DLC or DLN coating can further be doped with a transition metal. In particular W, Zr Ti, Nb and Ta are well suited as doping elements.

WO 2005/021851

PCT/EP2004/051998

3

The DLC or DLN coating can further contain an inert gas such as Ne, Ar or Kr, for example in an amount of 0.5 to 5 at%.

5 According to a second aspect of the present invention, a method of manufacturing a rapier is provided.

The method comprises the steps of

- providing a rapier;
- applying a hard metal based coating by thermal spraying.

10 To obtain a good adhesion, before the application of the hard metal based coating, the substrate is preferably pretreated by any technique known in the art as for example by grit blasting, grinding, milling, polishing or by a combination of these techniques.

15 A preferred method further comprises the step of

- applying a hard carbon coating.

The hard carbon coating such as a DLC or DLN coating is preferably applied by chemical vapour deposition.

20

It can be preferred to pretreat the rapier coated with the hard metal based coating before the application of the hard carbon coating.

This pretreatment may comprise for example grit blasting, grinding, milling, polishing or a combination of these techniques.

25

According to a third aspect of the invention a method to reduce the number of yarn ruptures during weaving is provided. The number of yarn ruptures is decreased by using a rapier as described above.

WO 2005/021851

PCT/EP2004/051998

4

Brief description of the drawings.

The invention will now be described into more detail with reference to the accompanying drawings wherein

- 5 - Figure 1 is a coated rapier according to the present invention.

Description of the preferred embodiments of the invention.

A rapier 10 according to the present invention is shown in figure 1.

10 The surface of the rapier 12 susceptible to wear due to the contact with the treads or yarn of the weaving machine of the rapier is coated with a thermal sprayed coating WC coating.

Before the application of the thermal sprayed coating, the rapier is pretreated by milling and polishing the surface to be coated.

15 In a next step a DLN coating is applied by chemical vapour deposition.

The WC coating has a thickness of 100 μm and a hardness of 1400 Vickers.

The WC coating has a roughness R_a of 4 μm .

20 Before the application of the DLN coating the rapier may be subjected to a milling and polishing operation until a surface roughness of 0.4 or 0.1 μm .

Wear on the rapier is strongly reduced because of the high wear resistance of the thermal sprayed hard metal based coating.

25 The low friction properties of the DLN coating reduce the number of yarn ruptures.

30 The life-time of a coated rapier according to the present invention is compared with the life-time of a rapier known in the art such as rapier coated with a hard chrome coating or rapier coated with a polymer coating. It has been shown that the life-time of a rapier according to the present invention is at least 2 till 3 times longer than the life-time of the rapier known in the art.

WO 2005/021851

PCT/EP2004/051998

5

CLAIMS

- 5
1. A rapier coated at least partially with a hard metal based coating, said coating having a hardness higher than 1000 Vickers.
2. A rapier according to claim 1, whereby said hard metal based coating is deposited by thermal spraying.
- 10
3. A rapier according to claim 1 or 2, whereby said hard metal based coating has a surface roughness Ra between 2 and 5 μm .
4. A rapier according to any one of the preceding claims, whereby said rapier is further coated with a hard carbon coating on top of said hard metal based coating.
- 15
5. A rapier according to any one of the preceding claims, whereby said hard carbon coating comprises a diamond-like carbon coating.
- 20
6. A rapier according to any one of claims 1 to 4, whereby said hard carbon coating comprises a diamond-like nanocomposite coating.
- 25
7. A method of manufacturing a coated rapier, said method comprising the steps of
- providing a rapier;
 - applying a hard metal based coating by thermal spraying.
- 30
8. A method according to claim 6, further comprising the step of
- applying a hard carbon coating.
9. A method according to claim 8, whereby said hard carbon coating is applied by chemical vapour deposition.

WO 2005/021851

PCT/EP2004/051998

6

10. A method to reduce the number of yarn ruptures during weaving by using a rapier as claimed in claim 1 to 6.

WO 2005/021851

1/1

PCT/EP2004/051998




Fig. 1

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP2004/051998

A. CLASSIFICATION OF SUBJECT MATTER IPC 7 D03D47/23 D03D47/12		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC 7 D03D		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the International search (name of data base and, where practical, search terms used) EPO-Internal, WPI Data, PAJ		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 6 230 759 B1 (COOPMAN LUCIEN ET AL) 15 May 2001 (2001-05-15) column 4, line 44 - line 48 -----	1,2,4,5, 7,8
Y	US 4 822 662 A (ISHII TAKASHI ET AL) 18 April 1989 (1989-04-18) column 1, line 7 - line 12 column 3, line 62 - column 4, line 22 column 9, line 47 - line 53 * table 1, samples 1 and 2 *	1,2,7
Y	EP 0 550 752 A (CITIZEN WATCH CO LTD) 14 July 1993 (1993-07-14) page 5, line 17 - line 22; figure 4 -----	4,5,8
A	US 4 757 844 A (PEZZOLI LUIGI) 19 July 1988 (1988-07-19) column 2, line 65 - column 3, line 4 ----- -/-	1,7
<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex.		
* Special categories of cited documents: "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the International filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the International filing date but later than the priority date claimed "T" later document published after the International filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "&" document member of the same patent family		
Date of the actual completion of the International search 18 November 2004		Date of mailing of the International search report 24/11/2004
Name and mailing address of the ISA European Patent Office, P.B. 5618 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016		Authorized officer Rebiere, J-L

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP2004/051998

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 99/29943 A (ROELSTRAETE KRISTOF ;PICANOL NV (BE)) 17 June 1999 (1999-06-17) page 4, lines 15-20; figures 1,4 -----	1,7

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP2004/051998

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 6230759	B1	15-05-2001	DE 19713628 A1	08-10-1998
			DE 59809213 D1	11-09-2003
			WO 9844180 A1	08-10-1998
			EP 0972099 A1	19-01-2000
US 4822662	A	18-04-1989	JP 2515281 B2	10-07-1996
			JP 61245346 A	31-10-1986
			JP 1890418 C	07-12-1994
			JP 6015733 B	02-03-1994
			JP 62006931 A	13-01-1987
			JP 62053443 A	09-03-1987
			JP 62060766 A	17-03-1987
			JP 62062960 A	19-03-1987
			CH 671034 A5	31-07-1989
			CN 86102733 A , B	17-12-1986
			KR 8901929 B1	31-05-1989
EP 0550752	A	14-07-1993	DE 69118705 D1	15-05-1996
			DE 69118705 T2	02-10-1996
			EP 0550752 A1	14-07-1993
			HK 22297 A	27-02-1997
			JP 2953673 B2	27-09-1999
			KR 9410803 B1	16-11-1994
			WO 9206234 A1	16-04-1992
			US 5511587 A	30-04-1996
US 4757844	A	19-07-1988	NONE	
WO 9929943	A	17-06-1999	BE 1011605 A3	09-11-1999
			WO 9929943 A1	17-06-1999